

## Technical Information

# GRAL<sup>®</sup> 204

emulsion of pure acrylate copolymer

<b>Technica Solid content approx. 50 %</b>
<b>pH value approx. 3.0</b>
<b>Viskosity EV ISO 3219 approx. 200 – 800 cP</b>
<b>Glass transition temperature approx. – 45 °C I data</b>

## Advantages:

Gral 204 forms a film medium tack medium peel strength and Excellent cohesion.

## Applications:

application devices such as dr blade, Meyer-bar, air brush, reverse roll, reverse gravure, curtain-coater and comma coating for product pe  
Protective film

## Storage:

store it at temperature between +5°C and +35°C.

Store in a original containers in a cool, dry area away from direct sunlight  
the product is stable at least 6 months from Production Manufacture Date.

## Packaging:

Drum of

- 20 kg
- 50 kg
- 100 kg
- 200 kg
- IBC Plastic Tank 1000 Kg