

Technical Information

GRAL® 820

emulsion of styrene acrylate copolymer

Technica Solid content approx. 50 %
pH value approx. 7.0 – 9.0
Viskosity EV ISO 3219 approx. 1000 – 1500 cP
Glass transition temperature approx. – 12 °C data

Advantages: soft and flexible film

Applications:

Acrylic Paints
Waterproof Coatings
adhesive
Primers

Storage:

store it at temperature between +5°C and +35°C.

Store in a original containers in a cool, dry area away from direct sunlight
the product is stable at least 6 months from Production Manufacture Date.

Packaging:

Drum of

- 20 kg
- 200 kg
- IBC Plastic Tank 1000 Kg