

## Technical Information

# GRAL® 141

emulsion of pure acrylate copolymer

<b>Technica Solid content approx. 60 %</b>
<b>pH value approx. 6.0 – 8.0</b>
<b>Viskosity EV ISO 3219 approx. 300 – 1000 cP</b>
<b>Glass transition temperature approx. – 70 °C I data</b>

## Advantages:

Gral 141 forms a film with very high tack, medium peel strength and low cohesion. It is used to manufacture pressure-sensitive adhesives, Insect adhesives and Tackifier

## Applications:

application devices such as dr blade, Meyer-bar, air brush, reverse roll, reverse gravure, curtain-coater and comma coating for product opp , pe , pvc tape , etc.

## Storage:

store it at temperature between +5°C and +35°C.

Store in a original containers in a cool, dry area away from direct sunlight the product is stable at least 6 months from Production Manufacture Date.

## Packaging:

Drum of

- 20 kg
- 200 kg
- IBC Plastic Tank 1000 Kg